

A17

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 09-175817

(43)Date of publication of application : 08.07.1997

(51)Int.Cl.

C01B 33/44
B01J 13/00
C08L 71/02
C09D 7/12
C09D171/02
// A61K 7/00
B05D 7/24

(21)Application number : 07-341293

(71)Applicant : CO-OP CHEM CO LTD

(22)Date of filing : 27.12.1995

(72)Inventor : SEKIMOTO TAKAHIRO

SAITO KANAKO

FUJISAKI TOSHIKAZU

ANDO SEINOSUKE

(54) SOL-GEL COMPOSITION

(57)Abstract:

PROBLEM TO BE SOLVED: To obtain a composition having uniform dispersibility, high viscosity and long-term stability in an organic solvent and/or polysiloxanes by blending an organic modified clay mineral obtained by introducing a specific quaternary ammonium ion into an intercalation of a swelling layered silicate with an anionic surfactant.

SOLUTION: The composition contains an organic modified clay mineral obtained by introducing a quaternary ammonium ion having polyoxyethylene group and/or a quaternary ammonium ion having polyoxypropylene group into intercalation of a swelling layered silicate and an anionic surfactant. The sol-gel composition is formed by dispersing the composition into an organic solvent and/or polysiloxanes. The swelling layered silicate includes e.g. a smectite based clay mineral or a swelling mica mineral.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of
rejection]